

Guideline for Storage and Handling

Handling



NedZink bright-rolled and preweathered material must be transported under dry and ventilated conditions. Avoid contact between the zinc surface and moisture during handling and transportation. Provide abrasion protection when transporting, avoid tight stacking and transport covered material on dry pallets. Due to the acidity of perspiration, fingerprints may become permanent blemishes if not removed quickly. When handling the NedZink material during transportation, fabrication and installation it is advised to wear gloves.

Storage

Store NedZink bright-rolled and preweathered material on dry pallets on a dry floor. While in storage contact between the zinc surface and moisture must be avoided. Provide ventilation to the covered materials. Allow materials to sit unopened for several days at the storage site to acclimation to the area's temperature and humidity before processing.

PE protective film for NedZink NOVA, -NEO, -NOIR and NUANCE

For special uses material with a single sided PE protective film on the finished side can be ordered. NedZink material is then provided with a transparent, self-adhesive PE-foil for additional protection of the surface during the application. This film protects the surface from damage and contamination during assembly or subsequent work. The protection is only functional when the film is not damaged. The adhesion of the film can be stronger in colder periods of the year. The PE protective film should be removed as soon as possible after installation. The temperature of the zinc should be at least 7 ° C. Below the 7 ° C temperature, the film cannot be removed. Do not remove the film partially as this may lead to unevenness of the patina and the formation of zinc hydroxide stains. It is not durable UV resistant and intended only for temporary protection. Rules for transportation and storing NedZink material:

	
	<p>Transportation: – Max. 4 pallets on each other for sheets</p>
	<p>– Please protect from getting wet</p>
	<p>– Has to be stored dry and ventilated – Please avoid condensation</p>
	<p>– NedZink NTZ can be recycled completely</p>

NedZink recommends a humidity of maximum 60-70% and a stable temperature of 12-14° Celsius. Please prevent from getting damaged.